

Latex Bonding Systems

Product Acceptance Criteria
Maine Department of Transportation – March 2006

These products shall meet the requirements of ASTM C 1059, Type II (non-redispersable) for bonding freshly mixed concrete to hardened concrete when tested in accordance with test method C 1042. Manufacturer shall clearly specify at the time of product submission that their product meets the requirements of this specification.

Physical Property Requirements

Latex	Bond Strength min. psi
Standards for latex bonding agents, Type II	1250